

ABS 0445E

ABS 0445E –is an extruded grade of general purpose with a good rigidity-hardness balance. It is used for production of sheets with high quality surface (co-extruded or not and with high extrusion ratio), applicable for refrigerators, sanitary, packaging, automobile parts, consumer goods and furniture (profiles).

It is produced self-colored only, free of additives and dye.

PROPERTY	Value	Test method
Melt flow rate, g/10min at 220 ⁰ C per 10 kg of load	4,0±1,5	ASTM 1238
Gloss at 60 ⁰ , minimum	60	ASTM D 523
Residual styrene mass fraction, %, not more	0,05	TY2214-159- 05766801-2011
Izod impact strength, notched, (4,0 mm, +23 ⁰ C) J/m, not less	15	ISO 180
Vicat softening temperature, (50 N, 50 ⁰ C/h), °C, not less	100	ASTM 1525
<i>Reference data</i>		
Tensile strength, MPa	45	ASTM D638
Strain at break, %	45	ASTM D638
Flexural strength, MPa	68	ASTM D790
Flexural modulus, MPa	2300	ASTM D790
Charpy impact strength, notched, kJ/m ² (+23 ⁰ C),	12	DIN 53453
Rockwell hardness	110	ISO2039/2
Deflection temperature under load, °C	104	ASTM D648
Coefficient of linear thermal expansion, 10 ⁻⁵ /°C	9	ASTM D696
Thermal conductivity, W/(K· m)	0,17	ASTM C177
Molding shrinkage, %	0,4-0,6	-
Flame behavior	HB	UL94
Glow wire test, °C	650	IEC 60695-2-1
Water absorption, %	0,3	ASTM D570

Product form:	Pallets
Packaging:	Polyethylene bags, in bulk by polymer trucks.
Transportation:	All types of covered transport.
Storage:	In closed room on shelves or pallets, at a distance of minimum 5 cm above the floor and at a distance of minimum 1 m from the space heaters, in conditions, excluding direct sunlight effect.

Information, stated in the specification, is submitted according to our data and is considered correct on the date of revision. This specification does not exempt the consumer from liability for checking the product correspondence to the suggested application. The producer is not responsible for any losses or damages, which can arise due to use of this information.