

ABS 0824V

ABS 0824V- is an easy flow, low gloss grade of special purpose, extruded and coextruded. It is widely used for production of foil extrusion/coextrusion that requires an enhanced mattness and for profile extrusion. It is produced self-colored , free of additives and dye.

PROPERTY	Value	Test method
Melt flow rate, g/10min at 220 ⁰ C per 10 kg of load	8,0±1,5	ASTM 1238
Gloss at 60 ⁰ , minimum	40	ASTM D 523
Residual styrene mass fraction, %, not more	0,05	TY2214-159- 05766801-2011
Izod impact strength, notched, (4,0 mm, +23 ⁰ C) J/m, not less	7	ISO 180
Vicat softening temperature, (50 N, 50 ⁰ C/h), °C, not less	97	ASTM 1525
<i>Reference data</i>		
Tensile strength, MPa	27	ASTM D638
Strain at break, %	100	ASTM D638
Flexural strength, MPa	40	ASTM D790
Flexural modulus, MPa	1550	ASTM D790
Charpy impact strength, notched, kJ/m ² (+23 ⁰ C),	9	DIN 53453
Rockwell hardness	97	ISO2039/2
Deflection temperature under load, °C	101	ASTM D648
Coefficient of linear thermal expansion, 10 ⁻⁵ /°C	9	ASTM D696
Thermal conductivity, W/(K· m)	0,17	ASTM C177
Molding shrinkage, %	0,4-0,6	-
Flame behavior	HB	UL94
Glow wire test, °C	650	IEC 60695-2-1
Water absorption, %	0,3	ASTM D570

Product form:	Pallets
Packaging:	Polyethylene bags, in bulk by polymer trucks.
Transportation:	All types of covered transport.
Storage:	In closed room on shelves or pallets, at a distance of minimum 5 cm above the floor and at a distance of minimum 1 m from the space heaters, in conditions, excluding direct sunlight effect.

Information, stated in the specification, is submitted according to our data and is considered correct on the date of revision. This specification does not exempt the consumer from liability for checking the product correspondence to the suggested application. The producer is not responsible for any losses or damages, which can arise due to use of this information.